



No.: SZTYR090202847/TS

Date: MAR 11, 2009

Page 1 of 5

SWIFTECH COMPANY LTD. BLOCK 6, ZHONGSHAN CIVIL SCIENCE & TECHNOLOGY PARK, ZHONGSHAN CITY, GUANGDONG PROVINCE, CHINA

The following samples were submitted and identified by/on behalf of the client as:

Name of Product/Item

SUPER CASTLE BOUNCER WITH SLIDE

Details of Sample Received:

INFLATABLE CANVAS CASTLE BOUNCER WITH SLIDE, COMES WITH 11 PLASTIC ANCHORS, 6 PIECES OF CANVAS SHEETS, 5 PIECES OF REPAIR PATCHES, 1 CARRYING BAG AND 2 INSTRUCTION SHEETS.

PRINTED BOX PACKED.

Sample Quantity

Style / Item No.

Manufacturer

Country of Origin Country of Destination

Labeled Age Grading

Requested Age Grading

Age Group Applied in Testing

Sample Receiving Date

Testing Period

: 1 PC

: 9217#

: SWIFTECH COMPANY LTD.

: CHINA

: USA & EN

: AGE RANGE 3 TO 10 YEARS

: 3+

: OVER 3 YEARS

: FEB 23, 2009

: FEB 23, 2009 TO MAR 09, 2009

Test Requested

For compliance with the European Standard on Safety of Toys:-

- EN71 Part 1:2005 +A4:2007 - Mechanical and Physical Properties

- EN71 Part 2:2006 +A1:2007 - Flammability of Toys

Pass Pass

Result

- EN71 Part 3:1994 +A1:2000 + AC:2002 - Migration of Certain Elements

<u>Pass</u>

Signed for and on behalf of SGS-CSTC Ltd.

Lin Shuzhen, Dora Lab Manager

HOKLAS Approved Signatories

Hong Kong Accreditation Service (HKAS) has accredited this laboratory under the Hong Kong Laboratory Accreditation Scheme (HOKLAS) for specific laboratory activities as listed in the HOKLAS directory of accredited laboratories. The results shown in this report were determined by this laboratory in accordance with its

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.
http://www.sgs.com/terms_and_conditions.
http://www.sgs.com/terms_and_conditions.
http://www.sgs.com/terms_and_conditions.htm
http://www.sgs.com/terms_and_conditions.htm
http://www.sgs.com/terms_and_conditions.htm
http://www.sgs.com/terms_a-document.htm
http://www.sgs.com/terms_a-document.htm
http://www.sgs.com/terms_a-document.htm
http://www.sgs.com/terms_a-document.htm
http://www.sgs.com/terms_a-document.htm
http://www.sgs.com/terms_a-document.htm
< esults shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

2,4,5/F, Oastar Building, Zhongkang Road, Shangmeilin, Shenzhen, China 518049 t (86–755) 83114358 f (86–755) 83106190 中国・深圳・上梅林中康路奥士达大厦2,4,5层

邮编: 518049 t (86-755) 83114358 f (86-755) 83106190 e sgs.china@sgs.com





No.: SZTYR090202847/TS

Date: MAR 11, 2009

Page 2 of 5

Results:

European Standard on Safety of Toys

- Mechanical and Physical Properties

AS SPECIFIED IN EUROPEAN STANDARD ON SAFETY OF TOYS EN71 PART 1: 2005 INCLUDING AMENDMENT 1 APPROVED BY CEN ON 2007-01-10, AMENDMENT 3 APPROVED BY CEN ON 2006-09-07, AMENDMENT 4 APPROVED BY CEN ON 2007-03-13 AND THE CORRIGENDUM ISSUED IN 2006.

<u>Clause</u>	<u>Description</u>	Result							
4	General requirements								
4.1	Material (by visual assessment)								
4.2	Assembled Toys								
4.7	Edges	<u>Pass</u>							
4.8	Points and Wires	<u>Pass</u>							
4.14	Enclosures:	<u>Pass</u>							
4.45	Toyo whom a office after	<u>Pass</u>							
4.15	Toys intended to bear the mass of a child:								
	4.15.4 Toys not propelled by a child	Pass							
5	Toys intended for children under 36 months								
5.1	General requirements								
	(Remark : Plastic sheet becomes detached as small part after test. It is acceptable	<u>See Remark</u>							
	because appropriate age warning was found on the packaging.)								
6	Packaging	<u>Pass</u>							
7	Warnings and instructions for use	. 4.55							
7.1	General Requirements	Page							
7.2	Toys not intended for children under 36 months	<u>Pass</u>							
—	. The metallicular of smarch and the months	<u>Pass</u>							

Hong Kong Accreditation Service (HKAS) has accredited this laboratory under the Hong Kong Laboratory Accreditation Scheme (HOKLAS) for specific laboratory activities as listed in the HOKLAS directory of accredited laboratories. The results shown in this report were determined by this laboratory in accordance with its terms of accreditation.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms and conditions. It is into another in the limitation of liability, in the limitation is used effined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its into the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exone rate parties to a transaction from exercising all their by this and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any smauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise titled that esuits shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. ss otherwise three tipe

1651112

2,4,5/F, Oastar Building, Zhongkang Road, Shangmeilin, Shenzhen, China 518049 t (86–755) 83114358 f (86–755) 83106190 中国・深圳・上梅林中康路奥士达大厦2,4,5层

es Co. Ltd.





No.: SZTYR090202847/TS

Date: MAR 11, 2009

Page 3 of 5

- Flammability of Toys

AS SPECIFIED IN EUROPEAN STANDARD ON SAFETY OF TOYS EN71 PART 2: 2006 INCLUDING CORRIGENDUM 1 ISSUED BY CEN ON 17 MAY 2006 AND AMENDMENT 1 APPROVED BY CEN ON 2007-02-08.

<u>Clause</u> 4.1 4.4	Description General Requirements Toys intended to be entered by a child	Result Pass Pass (See Note)
B.2. (

Note:

Toys Intended to be Entered by a Child (4.4)

<u>Sample</u> SUPER CASTLE BOUNCER Burning Rate (mm/sec) DNI

Flaming debris/Molten drips

No

WITH SLIDE

(The rate of spread of flame on the surface of toy shall not exceed 30 mm/sec or shall self-extinguish. There shall be no flaming debris or molten drips if the burn rate greater than 20 mm/sec.)

DNI = Did Not Ignite

- Migration of Certain Elements

AS SPECIFIED IN EUROPEAN STANDARD ON SAFETY OF TOYS EN71 PART 3 : 1994 (INCLUDES AMENDMENT A1:2000 AND AMENDMENT AC:2002) - MIGRATION OF CERTAIN ELEMENTS. ANALYSIS WAS PERFORMED BY INDUCTIVELY COUPLED PLASMA ATOMIC EMISSION SPECTROMETER.

Element		Pb	Sb	As	Ba	Cd	Cr	Hg	Se	Mass of
Soluble Limit (mg/kg)		90	60	25	1000	75	60	60	500	trace
Specimen Description		Adjusted Soluble Result (mg/kg)							amount (mg)	
1.	Red woven w/ white plastic sheet backing	<5	<5	<5	12	<5	<5	<6.7	<10	/
2.	Yellow woven w/ white plastic sheet backing	<5	<5	<5	<10	<5	<5	<6.7	<10	1
3.	Blue woven w/ white plastic sheet backing	<5	<5	<5	<10	<5	<5	<6.7	<10	1

Hong Kong Accreditation Service (HKAS) has accredited this laboratory under the Hong Kong Laboratory Accreditation Scheme (HOKLAS) for specific laboratory activities as listed in the HOKLAS directory of accredited laboratories. The results shown in this report were determined by this laboratory in accordance with its

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions. http://www.sgs.com/terms_and_conditions. http://www.sgs.com/terms_and_conditions.http://www.sgs.com/terms_and_conditions.http://www.sgs.com/terms_and_conditions.http://www.sgs.com/terms_and_conditions.http://www.sgs.com/terms_and_conditions.http://www.sgs.com/terms_and_conditions.http://www.sgs.com/terms_and_conditions.http://www.sgs.com/terms_and_conditions.http://www.sgs.com/terms_and_conditions.http://www.sgs.com/terms_and_conditions.http://www.sgs.com/terms_and_conditions.http://www.sgs.com/terms_and_conditions.http://www.sgs.com/terms_and_conditions.http://www.sgs.com/t esults shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

www.cn.sgs.com

2,4,5/F, Oastar Building, Zhongkang Road, Shangmeilin, Shenzhen, China 518049 t (86-755) 83114358 f (86-755) 83106190 中国・深圳・上梅林中康路奥士达大厦2,4,5层 邮编: 518049 t (86-755) 83114358 f (86-755) 83106190 e sgs.china@sgs.com





No.: SZTYR090202847/TS

Date: MAR 11, 2009

Page 4 of 5

Element		Pb	Sb	As	Ва	Cd	Cr	Hg	Se	Mass of
Soluble Limit (mg/kg)		90	60	25	1000	75	60	60	500	trace
Specimen Description			Adjusted Soluble Result (mg/kg)							
4.	Blue plastic sheet w/ white mesh inside	<5	<5	<5	11	<5	<5	<6.7	<10	(mg) /
<u>5</u> .	Green fabric (Warning label)	<5	<5	<5	<10	<5	<5	<6.7	<10	/
6.	Yellow fabric (Warning label)	<5	<5	<5	<10	<5	<5	<6.7	<10	1
7.	Blue velcro	<5	<5	<5	<10	<5	<5	<6.7	<10	1
8.	Red velcro	<5	<5	<5	<10	<5	<5	<6.7	<10	1
9.	Yellow velcro	<5	<5	<5	<10	<5	<5	<6.7	<10	1
10.	Black coating on woven (Logo)	<5	<5	<5	<10	<5	<5	<6.7	<10	1
11.	Blue coating on woven (Logo)	<5	<5	<5	<10	<5	<5	<6.7	<10	14.6
12.	Yellow coating on woven (Logo)	<5	<5	<5	<10	<5	<5	<6.7	<10	1
13.	Red coating on woven (Logo)	<5	<5	<5	78	<5	<5	<6.7	<10	/
14.	Black plastics (Buckle)	<5	<5	<5	<10	<5	<5	<6.7	<10	1
15.	Red printed yellow fabric (Warning label)	<5	<5	<5	<10	<5	<5	<6.7	<10	89.3
16.	Yellow plastics (Stake)	<5	<5	<5	<10	<5	<5	<6.7	<10	1
17.	Transparent adhesive plastic sheet (Repair patch)	<5	<5	<5	<10	<5	<5	<6.7	<10	1
18.	Red woven band (Handle)	<5	<5	<5	<10	<5	<5	<6.7	<10	1
19.	Red woven band (Binding)	<5	<5	<5	<10	<5	<5	<6.7	<10	1
20.	Black mesh (Thick)	<5	<5	<5	<10	<5	<5	<6.7	<10	1
21.	Black woven band (Binding)	<5	<5	<5	<10	<5	<5	<6.7	<10	1

- < = Less than
- Results shown are of the adjusted analytical results.

Only applicable clauses were shown.

Hong Kong Accreditation Service (HKAS) has accredited this laboratory under the Hong Kong Laboratory Accreditation Scheme (HOKLAS) for specific laboratory activities as listed in the HOKLAS directory of accredited laboratories. The results shown in this report were determined by this laboratory in accordance with its terms of accreditation.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.
but and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, in the limits of and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its into realistic singular there is instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from the exercising all there, that and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any shauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise attent to the sample(s) tested and such sample(s) are retained for 30 days only.

2,4,5/F, Oastar Building, Zhongkang Road, Shangmeilin, Shenzhen, China 518049 t (86–755) 83114358 f (86–755) 83106190 中国・深圳・上梅林中康路奥士达大厦2,4,5层

邮编: 518049 t (86-755) 83114358 f (86-755) 83106190 e sgs.china@sgs.com





No.: SZTYR090202847/TS

Date: MAR 11, 2009

Page 5 of 5

Sample Photo:



SGS authenticate the photo on original report only

*** End of Report ***

Hong Kong Accreditation Service (HKAS) has accredited this laboratory under the Hong Kong Laboratory Accreditation Scheme (HOKLAS) for specific laboratory activities as listed in the HOKLAS directory of accredited laboratories. The results shown in this report were determined by this laboratory in accordance with its terms of accreditation.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms and conditions.

http://www.sgs.com/terms e-document.htm. Attention is drawn to the limitation of liability, potentials than and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of a feethire.

The state of the state within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction this and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. The company of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. specification and the esults shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

2,4,5/F, Oastar Building, Zhongkang Road, Shangmeilin, Shenzhen, China 518049 t (86–755) 83114358 f (86–755) 83106190 中国・深圳・上梅林中康路奥士达大厦2,4,5层